



## Modelling holographic signals from ferroelectric nanostructures and polar interfaces

**Beleggia, Marco**

*Published in:*

Proceedings of the 15th Frontiers of Electron Microscopy in Materials Science

*Publication date:*

2015

*Document Version*

Peer reviewed version

[Link back to DTU Orbit](#)

*Citation (APA):*

Beleggia, M. (2015). Modelling holographic signals from ferroelectric nanostructures and polar interfaces. In *Proceedings of the 15th Frontiers of Electron Microscopy in Materials Science*

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

# Modelling holographic signals from ferroelectric nanostructures and polar interfaces

Marco Beleggia<sup>1,2</sup>

<sup>1</sup>Center for Electron Nanoscopy, Technical University of Denmark, 2800 Kgs. Lyngby, Denmark

<sup>2</sup>Helmholtz-Zentrum Berlin für Materialien und Energie, 14109 Berlin, Germany

E-mail: mb@cen.dtu.dk

Electron holography experiments carried out on polar materials have proven extremely challenging [1,2]: contrary to ferromagnets, where the electron beam is affected --phase shifted or deflected-- by the magnetization, polarization alone is invisible to phase-sensitive techniques. The origin of this fundamental difference can be traced back to the Lorentz force: magnetic deflections are proportional to the B-field, of which  $M$  is an integral part, while electric deflections are proportional to the E-field; an electric field might as well be generated by bound polarization charges if present, but with a non-linear and, in a sense, non-local relationship as polarization charges may be very far away from the illuminated region of the sample. Moreover, the absence of magnetic monopoles combined with quantization of angular momentum, which applies only to spins and not to electric dipoles, results in screening/depolarizing effects manifesting themselves very differently in magnetic and electric polar materials.

In nanoparticles made of materials that are ferroelectric in bulk form, the polarization is suppressed by its own depolarization field [3]. To preserve  $P$  below a certain critical size, screening of the depolarization field must occur. Screening can be internal --redistribution of mobile charges in metallic or oxygen-vacant insulating ferroelectrics-- or external in case of embedment in a dielectric or metallic matrix. However, if the screening is 100% effective so that the bulk  $P$  value is sustained in finite-size structures, the internal electric field vanishes entirely, giving rise to no observable holographic signal. A trade-off needs to be found between screening capacity and magnitude of the resulting polarization that maximizes the residual internal field deflecting the incoming electron beam, and resulting in observable phase shifts. This trade-off will be discussed, highlighting realistic and achievable experimental conditions that may facilitate the success of electron holography experiments on ferroelectric nanostructures.

In case of polar interfaces [4], for example a ferroelectric layer sandwiched in between dielectrics, or heterostructures involving charge-layered oxide materials such as  $\text{LaAlO}_3$  in contact with doped or undoped  $\text{SrTiO}_3$  where a 2D electron gas may emerge, determining whether or not we can expect a phase shift is a difficult task. In addition to self-depolarization, particularly strong in parallel-plate-capacitor situations where the depolarization factor approaches unity, we need to handle the band structure relaxation bringing extra mobile charges into the picture: charge transfer may occur even with insulators, if band bending is so severe that the chemical potential dips into their valence band. A test scenario involving two ferroelectrics with different bulk polarizations, with and without chemical potential shift will be presented to illustrate the complexity of the problem, and to provide an initial framework for the interpretation of holographic signals from polar interfaces.

## References:

- [1] D. Szwarcman et al., Phys. Rev. B 85, 134112 (2012)
- [2] M.J. Polkin et al., Nature Materials 11, 700 (2012)
- [3] C. Phatak et al., Phys. Rev. B 89, 214112 (2014)
- [4] N. Nakagawa et al., Nature Materials 5, 204 (2006)